



1.2085

<u>Corrispondenze</u> <u>Comparable standards</u>	UNI ~X33CrS16	AISI ~420F	WERKSTOFF 1.2085	SIGLE DI MERCATO ~M314 – UK02S				
<u>Composizione</u> <u>indicativa</u> <u>Chemical analysis</u> <u>indicative</u>	C	Si	Mn	Cr	Mo	Ni	V	S
	0,33	0,50	1,00	16,00		0,70		0,10

<u>Caratteristiche generali e impieghi</u> Acciaio inossidabile martensitico resistente alla corrosione - buona resistenza meccanica e tenacità; - eccellente per la fabbricazione di componenti che devono resistere a plastiche corrosive / abrasive; - ottima lavorabilità all'utensile dovuta al contenuto di zolfo; - atto a lavorare in presenza di atmosfera umida e acqua di condensa; - idoneo alla resistenza all'usura e alla corrosione; - molto stabile dimensionalmente in fase di trattamento termico; - applicazioni: stampi e porta stampi per l'industria della plastica es. PVC;	<u>Main characteristics and applications</u> Alloyed stainless martensitic chromium steel with high corrosion resistance, with very good machinability, uniform strength within the whole cross-section at all dimensions and good mechanical damage resistance. It is a modification of steel 1.2316 with sulfur addition, due to which steel 1.2085 features higher machinability. The steel is supplied in treated condition and there is no need for subsequent heat treatment (the delivered condition is exploited). Subsequent heat treatment is recommended only in exceptional events when higher hardness is required. The steel is suitable for moulds frameworks of all dimensions, above all for chemically aggressive plastic materials processing and for moulds working in humid climatic conditions. The steel is not suitable for shaped parts forming a part's outline.
<u>Stato di fornitura</u> Bonificato HB 280÷325	<u>Supply Condition</u> Hardened and tempered HB 280÷325
<u>Sagomario</u> Lamiere fino a spessore 500 mm	<u>Shape</u> Sheets up to 500 mm